



BLIND RIVET SOLUTIONS

**GOLD COAST: Unit 1/13 John Duncan Crt
Varsity Lakes QLD 4227
Tel: 07 5593 4550 Fax: 07 5593 4549
email: coastsales@aerofast.com.au
ABN: 23 068 361 455 www.aerofast.com.au**



HIGH GRADE
**TRUSS HEAD DOME HEAD
MONEL**

60% NICKEL 40% COPPER / STEEL

Part No	Body	Mandrel	Body Dia. mm	Grip Range mm	Recommended mm	Body Length mm	Clearance mm	Head Dia. mm	Shear (N)	Tensile (N)	Inner Qty	Outer Qty
73MS41	NI/CU	Steel	3.2 (1/8)	Up to 1.6	3.3	5.15	7.4	6.65	1560	2000	1000	10000
73MS42	NI/CU	Steel	3.2 (1/8)	1.6-3.2	3.3	6.85	9.1	6.65	1560	2000	1000	10000
73MS43	NI/CU	Steel	3.2 (1/8)	3.2-4.8	3.3	8.35	10.6	6.65	1560	2000	1000	10000
73MS44	NI/CU	Steel	3.2 (1/8)	4.8-6.4	3.3	9.95	12.2	6.65	1560	2000	1000	10000
73MS45	NI/CU	Steel	3.2 (1/8)	6.4-7.9	3.3	11.55	13.8	6.65	1560	2000	1000	10000
73MS46	NI/CU	Steel	3.2 (1/8)	7.9-9.5	3.3	13.45	15.7	6.65	1560	2000	1000	10000
73MS52	NI/CU	Steel	4.0 (5/32)	1.6-3.2	4.1	7.45	10.2	8.45	2450	3110	1000	10000
73MS53	NI/CU	Steel	4.0 (5/32)	3.2-4.8	4.1	9.05	11.8	8.45	2450	3110	1000	10000
73MS54	NI/CU	Steel	4.0 (5/32)	4.8-6.4	4.1	10.55	13.3	8.45	2450	3110	1000	10000
73MS55	NI/CU	Steel	4.0 (5/32)	6.4-7.9	4.1	12.05	14.8	8.45	2450	3110	1000	10000
73MS56	NI/CU	Steel	4.0 (5/32)	7.9-9.5	4.1	13.75	16.5	8.45	2450	3110	500	5000
73MS62	NI/CU	Steel	4.8 (3/16)	1.6-3.2	4.9	8.05	11.05	10	3200	4450	500	5000
73MS63	NI/CU	Steel	4.8 (3/16)	3.2-4.8	4.9	9.65	12.65	10	3200	4450	500	5000
73MS64	NI/CU	Steel	4.8 (3/16)	4.8-6.4	4.9	11.25	14.25	10	3200	4450	500	5000
73MS65	NI/CU	Steel	4.8 (3/16)	6.4-7.9	4.9	12.85	15.85	10	3200	4450	500	5000
73MS66	NI/CU	Steel	4.8 (3/16)	7.9-9.5	4.9	14.45	17.45	10	3200	4450	500	5000
73MS68	NI/CU	Steel	4.8 (3/16)	9.5-12.7	4.9	17.55	20.55	10	3200	4450	500	5000
73MS610	NI/CU	Steel	4.8 (3/16)	12.7-15.9	4.9	21.45	24.45	10	3200	4450	500	5000



The **Monel / Steel Truss Head** range is made from heading quality 400HQ grade Monel wire with a medium carbon content, zinc plated, steel mandrel to suit those applications where high tensile strengths and corrosion resistance are required. Manufactured by Spurway Cooke in Singapore, using only the highest quality wire consisting of 60%Nickel and 40% copper, you can be assured of the highest consistency and quality. This range is commonly used where Stainless Steel is not suitable as it has similar corrosion resistance and tensile strengths.